

**OUR SUPER SOFT WATER BASED HTV**

This water based PU uses zero solvent in its production process giving it a matte finish and super soft touch. This is applicable on all types of garments / textiles, such as cotton, polyester, acrylic and nylon.



**APPLICATION INSTRUCTIONS**

- STEP 1** - Set design to cut
- STEP 2** - Easily weed excess material
- STEP 3** - Set heat, time, pressure
- STEP 4** - Pre-press garment
- STEP 5** - Apply then peel hot or cold

**SPECIFICATIONS**

<b>WATER BASED</b>	Yes
<b>COMPOSITION</b>	Solvent Free PU
<b>THICKNESS</b>	90 micron
<b>CARRIER</b>	Medium-Tack Clear Polyester
<b>CUTTING</b>	Flex 45° blade
<b>CERTIFICATIONS</b>	OEKO TEX std 100 Class I: All references Class II: Ref 3602 Vegan
<b>APPLICATIONS</b>	Cotton, Polyester, Acrylic, Cotton/ Polyester blends, Nylon (Polyamide) No repellent treatment
<b>TEMPERATURE</b>	285°F / 140°C 5 Sec Quick Mode 250°F / 120°C 20 Sec Low Temp <i>Specific textiles:</i> Nylon 1st press 285°F / 140°C 5 Sec Peel carrier Hot or Cold 2nd press 285°F / 140°C 15 Sec
<b>PRESSURE</b>	Medium
<b>PEEL</b>	Hot or Cold

**PRODUCT HIGHLIGHTS**

- Water based and solvent free PU
- Super soft matte finish
- Perfect for multiple garment applications
- Easy to cut, weed and peel hot or cold
- Suitable for all types of fabrics, including nylon
- Suitable for baby / kids clothing and sportswear
- Super flexible, great for stretchable garments

**CARE & MAINTENANCE**

- Always respect the garment instructions
- Wash warm up to 140°F/60°C or 100°F/40°C for Nylon
- Allow 24 hours after application before first wash
- Avoid the use of strong chemicals, do not bleach
- Wash inside out to extend the design's life
- Storage life recommendation is up to one year
- Store product in dry room with 60°-85°F / 15°-30°C
- Keep away from sunlight in a vertical position

**NOTE:** We highly recommend that you perform tests before production.



**Chemica US Corp.**

5300 Oakbrook Parkway | Building 300, suite 368 | Norcross, GA 30093 USA  
T +1 404-495-5991 | info@chemicaus.com | www.chemica-us.com